


Samples of each membrane are cut and weighed, immersed in the chemical for seven days at 73°F (23°C), removed, cleaned and re-weighed.

Reported values reflect change in weight after the seven day exposure, as measured at 15 minutes and 24 hours after removal.

# HEXANE



Testing simulates the effect of chemical contamination on a roofing membrane.

Changes in weight gain or loss illustrate the extent of a roofing membrane's ability to resist exposure to a chemical contaminant.

Weight loss is associated with plasticizer extraction or the loss of other compound additives.

Weight gain is indicative of a contaminant's ability to permeate the membrane causing swelling and/or softening of the compound.

% Weight Change



**INTELLIGENT**  
ROOFING SOLUTIONS

For more information on FiberTite Systems and Accessories please call: Seaman Corporation (800) 927-8578, International (330) 262-1111. [www.fibertite.com](http://www.fibertite.com)

FiberTite® is a registered trademark of Seaman Corporation.

Elvaloy® is a registered trademark of DuPont.